



TEST REPORT

Client P.P. O'Connor Ltd

Address 61 Mosley Road
Trafford Park
Manchester
M1 1GJ

Contract Manchester Airport

Job Number MRN 3845/26
Date of Issue 30 July 2020
Page 1 of 4

Approved Signatories

S J Hutchings, O P Davies

Notes

- 1 All remaining samples and remnants from this contract will be disposed 28 days from the date of this report unless you notify us to the contrary.
- 2 Result certificates, in this report, not bearing a UKAS mark, are not included in our UKAS accreditation schedule.
- 3 Opinions and interpretations expressed herein are outside the scope of our UKAS accreditation
- 4 Certified that the samples have been examined and tested in accordance with the terms of the contract/order and unless otherwise stated conform to the standards/specifications quoted. This does not, however, guarantee the balance of the materials from which the tested samples have been taken to be of equal quality.



Andrew House, Hadfield Street, Dukinfield, Cheshire SK16 4QX Tel: 0161 475 0870
Email: enquiries@murrayrix.com Website: www.murrayrix.com

Also at: London: 020 8523 1999

Murray Rix is the trading name of Murray Rix (Northern) Limited. Registered in England 2878361

MURRAY RIX

ANDREW HOUSE, HADFIELD STREET,
DUKINFIELD, CHESHIRE SK16 4QX
TEL 0161 475 0870



TEST CERTIFICATE

PARTICLE SIZE DISTRIBUTION

BS 1377: PART 2: Clause 9.2: 1990


Determination of Moisture Content in accordance with BS 1377: PART 2: Clause 3: 1990 (Oven Dry)

CLIENT	P.P. O'Connor Ltd
SITE	Manchester Airport
JOB NUMBER	MRN 3845/26

SAMPLE LABEL	Sample 3	DATE SAMPLED	Not advised
LAB SAMPLE No	90657	DATE RECEIVED	16-Jul-20
DATE TESTED	16-Jul-20	SAMPLED BY	Client

MATERIAL	Recycled Material
ADVISED SOURCE	As client and site above

Sieve Size (mm)	% Passing (%)	Specification (%)	Sieve Size (mm)	% Passing (%)	Specification (%)
125	100	100	10	43	15-60
90	100	80-100	5	32	10-45
75	92	65-100	2	22	
50	80		0.6	15	0-25
37.5	72	45-100	0.3	10	
20	55		0.15	8	
14	48		0.063	7	0-12



REMARKS

Sample complies with the grading requirements for a 6F2 material (SHW 2016)
As received moisture content = 5.2%

SIGNED

NAME

O.P. Davies BA (Hons)
(Laboratory Manager)

DATE

30-Jul-20