

Laboratory Report	DNR/6764	Contract Sample No	C3783/92								
Report Date	09/08/2019	Clients Reference	C3783/92								
Ballast Phoenix Ltd Victoria Stables South Road Bourne Lincolnshire PE10 9JZ Johnsons Lane, Widnes		Material Description Source Supplier Date Sampled Date Received Date Completed Sample Location	T1SB IBAA Johnsons Lane Ballast Phoenix 15/07/2019 15/07/2019 29/07/2019 Stockpile								
 Construction Testing Solutions Ltd Bootham Lane Industrial Estate Dunscroft Doncaster DN7 4JU T (01302) 352652 E enquiries@constructiontesting.co.uk W www.constructiontesting.co.uk  4161											
Determination of Plastic Limit, Liquid Limit and Plasticity Index - BS 1377: Part 2: 1990 The sample was prepared from a wet sieved specimen and in accordance with BS1377: Part 1: 1990: Clause 7.3.4(b)											
<table> <tr> <td>Liquid Limit (BS 1377: Part 2: 1990 Clause 4.4 - One Point)</td> <td>62 %</td> </tr> <tr> <td>Plastic Limit (BS 1377: Part 2: 1990 Clause 5.3)</td> <td>N/P %</td> </tr> <tr> <td>Plasticity Index (BS 1377: Part 2: 1990 Clause 5.4)</td> <td>N/A %</td> </tr> <tr> <td>Material Passing 425 µm test sieve</td> <td>13 %</td> </tr> </table>				Liquid Limit (BS 1377: Part 2: 1990 Clause 4.4 - One Point)	62 %	Plastic Limit (BS 1377: Part 2: 1990 Clause 5.3)	N/P %	Plasticity Index (BS 1377: Part 2: 1990 Clause 5.4)	N/A %	Material Passing 425 µm test sieve	13 %
Liquid Limit (BS 1377: Part 2: 1990 Clause 4.4 - One Point)	62 %										
Plastic Limit (BS 1377: Part 2: 1990 Clause 5.3)	N/P %										
Plasticity Index (BS 1377: Part 2: 1990 Clause 5.4)	N/A %										
Material Passing 425 µm test sieve	13 %										
Aggregate Sampled in Accordance with BSEN 932-1 : 1997											
Authorised Signatory  P Nodder - Technical Director											