



Method Statement for Tiled Vestibule Floor

Author:

Mark Kelly

Location of works:

Manchester Jewish Museum

Brief Description: Method statement for the tiled floor to entrance vestibule.

Materials:

The materials used as per specification of manufacturer: Hadley Reclaimed tiles, Ardex tile bedding mortar, Hanson Cement grout & Lithofin KF Stainstop

- Self-levelling compound
- Quarry tiles red/blue unglazed
- Ardex S 21 rapid hardening floor tile bedding mortar & Ardex E90 admix
- Hanson Cement CEM I 52.5N
- Building sand
- Lithofin KF Stainstop

Methodology:

- Firstly, the old paint surfaces will be lightly sanded with all flaky, peeling or bubbling paint removed with a paint scraper.
- Where required blend and 'feather' the edges of areas of old paint, as this helps to smooth out the surface.
- Any scratches, indentations etc. shall be filled with an appropriate filler.
- All surfaces shall again be lightly sanded.
- All surfaces will then be cleaned with sugar soap to make sure they are sound, clean, dry and free from dirt, grease and other contamination.
- Any areas needing further treatment to bare knotty or resinous areas shall be patch primed with wood knot & resin blocking primer

- After allowing sufficient time for the wood knot & resin blocking primer to dry apply one coat of exterior wood primer & undercoat, in the correct colour tone for your top coat (and allowing a minimum of 4 hours drying time between coats).
- Then apply two coats of your chosen exterior eggshell in the specified colour, allowing the correct drying time between coats
- Metal door runners at both the head and base of the door will be cleaned, paying particular attention to the grooved runners.
- Clean and remove debris and oil to tiled floor area
- Fill in matwell area with self-levelling compound leaving adequate time for it to dry out.
- Quarry tiles to be impregnated before installation with Lithofin KF Stainstop
- Apply Ardex S 21 rapid hardening floor tile bedding mortar & Ardex E90 admix to the previously prepped floor area then lay the reclaimed quarry tiles.
- Once the quarry tiles have been installed and left to set to the manufacturers recommendations the grout can be applied (Hanson Cement CEM I 52.5N * building sand to a 4:1 ratio)
- Once grout has set quarry tiles shall be sealed with Lithofin KF Stainstop.

