EDENHALL

HOWLITE GREY

FACING BRICKS




TECHNICAL DATA

CONFIGURATION	Perforated
SIZE	215 x 15 x 65 (+3-5mm)
DENSITY	2200kg/m3 average
STRENGTH	22N2/mm2 minimum average
MOISTURE ABSORBTION	6-8% typical average
DURABILITY	Fully frost resistant

FULL TECHNICAL SPECIFICATION AVAILABLE UPON REQUEST







EDENHALL

Central Sales **01244 677199**

Southern Sales **01633 600806**

sales@edenhall.co.uk

www.edenhall.co.uk

Disclaimer: The Sample is intended to show the general colour and texture of the product. Slight variations may occur due to the manufacturing process and inherent properties of the constituent natural raw materials. Where tight aesthetic tolerances are important we would strongly recommend a more comprehensive sample approval process is adopted. The colours on this data sheet are accurate as modern printing processes will allow. You are advised to see actual brick samples before ordering.