MORTAR ANALYSIS REPORT

JOB REFERENCE	**India House**	SAMPLE	**7**	PAGE **1**

ANALYSIS DATE	**September 2024**
SITE	**India House, Manchester**
CLIENT	**Bernard Taylor Partnership**
DATE/ TAKEN RECEIVED	**September 2024**
CLIENT REQUIREMENTS	**Analyse mortar sample**
LOCATION/ FUNCTION IN BUILDING	**India House Turret 2**
CONDITION OF SAMPLE RECEIVED/ COLLECTED	**Bound mortar**

GENERAL COMMENTS/ SUMMARY

The nature of the binding matrix of the mortar sample and information gained from the analysis suggest that the mortar was probably made by weight from 1 part moderately hydraulic lime to 2.5 parts very fine-graded quartz-based sand. The ash in the mortar comes from the lime production process. A mix by volume of 1 part lime to 2 parts aggregate would be appropriate for tighter joints.

MORTAR ANALYSIS REPORT

JOB REFERENCE	**India House**	SAMPLE	**7**	PAGE **2**

ANALYTICAL PROCEDURES

The selected material sample was dried, weighed, and examined both by eye and under a binocular microscope at x 20 and x 35 magnification. The sample was crushed, and the binder was separated from the aggregate by dissolution in dilute hydrochloric acid. The relative proportions of binder (lime, cement, and gypsum) to aggregate were determined. Aggregate (and other acid-insoluble materials) characterisation was undertaken utilising sieve separation and further microscopic examination.

The analysis and interpretation provide information on the composition and characteristics of the mortar sample(s) received. Assuming that the sample was generally representative of the mortar, the analysis will give a reasonable indication of the original materials and provide a basis for the specification of repair or replacement mortars.

If more detailed information is required (for example, for historical research purposes), more sophisticated analytical procedures can be undertaken to determine chemistry and mineralogical composition.

MORTAR EXAMINATION AND ANALYSIS

PROCEDURE	**DESCRIPTION / COMMENTS**
PRELIMINARY EXAMINATION OF SAMPLE BY EYE	A fine-grained, cream-coloured mortar with clinker fragments
EXAMINATION OF PREPARED SAMPLE BY BINOCULAR MICROSCOPE x20 MAG	The mortar has an open texture. It contains clear, pink and iron-stained quartz and clinker ash in a rich cream binder.

MORTAR ANALYSIS REPORT

JOB REFERENCE	**India House**	SAMPLE	**7**	PAGE **3**

ACID DISSOLUTION

PROCEDURE	**DESCRIPTION ~ COMMENTS**
10% HCL ACID DISSOLUTION	It is relatively easy to crush. There was an initial strong reaction upon dissolution.
FILTER GRADE (PORE SIZE) & TYPE	Whatman Type 1

AGGREGATE SEPARATION

BS SIEVE Mesh Size	**Residue Retained in g's**	**Undissolved binder %**	**Aggregate wt excluding undissolved binder - gs**	**Aggregate weight %**	**Comments**
4.75 mm	0				
2.36 mm	0				
1.18 mm	0.04	30	0.03	n/a	Clear, pink and iron-stained quartz & clinker ash and terracotta fragments
0.60 mm (600 μm)	0.14	20	0.11	n/a	Clear, pink and iron-stained quartz & clinker ash and terracotta fragments
300 μm	1.87	4	1.8		Clear and pink quartz & clinker ash fragments
150 μm	0.58	10	0.52		Clear and pink quartz, & clinker ash fragments.
< 150 μm, including filter residue	0.12	20	0.1		Clear and pink quartz and clinker ash. Mainly Belite binder residue.

All the quartz aggregate is sub-rounded.

MORTAR ANALYSIS REPORT

JOB REFERENCE	**India House**	SAMPLE	**7**	PAGE **4**

AGGREGATE CHARACTERISTICS

Clear quartz-based sand and ash formed the primary aggregates.

Because sand and gravel aggregates are ultimately derived from the weathering of solid rock, most aggregates contain coarse-grained rock fragments and finer mineral grains. Weathering breaks down the rock fragments within the aggregate into the constituent minerals, resulting in smaller and rounder particles; chemical weathering breaks down unstable minerals, such as feldspars, into clays which may be washed away, both processes eventually result in a quartz-rich sand.

CONSTITUENTS OF ANALYSIS SAMPLE

MATERIAL	***WEIGHT (g)***	**COMMENTS**
A: DRY WEIGHT OF-ANALYSIS SAMPLE	3.64	
B: DRY WEIGHT OF ALL INSOLUBLE	2.75	
C: DRY WEIGHT OF INSOLUBLE BINDER	0.19	
D: (B-C) DRY WEIGHT OF AGGREGATE	2.56	
E: (A-B+C)) DRY WEIGHT OF LIME & BINDERS	1.08	
F: DRY WEIGHT OF LIME	0.89	
OTHER		

MORTAR ANALYSIS REPORT

JOB REFERENCE	**India House**	SAMPLE	**7**	PAGE **5**

PROPORTIONS OF ANALYSIS SAMPLE

The sample proportions give aggregate and carbonated or set lime relative weights.

LIME BINDER: AGGREGATE

1: 2.4

With 18% hydraulic binder content to the volume of lime

PROBABLE ORIGINAL MIX

The nature of the binding matrix of the mortar sample and information gained from the analysis suggest that the mortar was probably made by weight from 1 part moderately hydraulic lime to 2.5 parts very fine-graded quartz-based sand. The ash in the mortar comes from the lime production process.

Sample analysis, interpretation and report carried out by: Mark Womersley.
www.mwomersleys.co.uk