




LANCASHIRE BRICK & TILE

Orlando House
67 Manchester Road
Bolton BL2 1ES
Tel: (01204) 400400
Fax: (01204) 404040
e-mail: sales@lancashirebrick.co.uk

Technical Data Sheet

Telford Red Smooth



Durability:	F2 to BS EN 771-1:2003
Compressive Strength:	> 70 N/mm ²
Water Absorption:	< 7 %
Soluble Salts:	S2
Brick Size:	215x102.5x73mm
No. Brick per Pack:	336 no.
Weight per Pack:	1.100 tonnes
Coverage:	approx. 53/m ²