MORTAR ANALYSIS REPORT

JOB REFERENCE	**India House**	SAMPLE	**1**	PAGE **1**

ANALYSIS DATE	**June 2026**
SITE	**India House**
CLIENT	**Recclesia**
DATE/ TAKEN RECEIVED	**June 2026**
CLIENT REQUIREMENTS	**Mortar analysis**
LOCATION/ FUNCTION IN BUILDING	**Low-level pointing**
CONDITION OF SAMPLE RECEIVED/ COLLECTED	**Bound sample**

GENERAL COMMENTS/ SUMMARY

The nature of the binding matrix of the mortar sample and information gained from the analysis suggest that the mortar was probably made by volume from 1 part early cement, 2 ½ parts hydrated lime (including much inert lime), and 5 parts waste clinker ash.


MORTAR ANALYSIS REPORT

JOB REFERENCE	**India House**	SAMPLE	**1**	PAGE **2**

ANALYTICAL PROCEDURES

The selected material sample was dried, weighed, and examined by eye and under a binocular microscope at x 20 and x 35 magnification. The sample was crushed, and the binder was separated from the aggregate by dissolution in dilute hydrochloric acid. The relative proportions of binder (lime, cement, and gypsum) to aggregate were determined. Aggregate (and other acid-insoluble materials) characterisation was undertaken utilising sieve separation and further microscopic examination. The analysis and interpretation provide information on the composition and characteristics of the mortar sample(s) received. Assuming that the sample was generally representative of the mortar, the analysis will give a reasonable indication of the original materials and provide a basis for the specification of repair or replacement mortars.
If more detailed information is required (for example, for historical research purposes), more sophisticated analytical procedures can be undertaken to determine chemistry and mineralogical composition.

MORTAR EXAMINATION AND ANALYSIS

PROCEDURE	**DESCRIPTION / COMMENTS**	
PRELIMINARY EXAMINATION OF SAMPLE BY EYE	A fine-grained, dusty mid-grey ash mortar with visible clinker and small lime inclusions.	
EXAMINATION OF PREPARED SAMPLE BY BINOCULAR MICROSCOPE x20 MAG	The fine-grained binder-rich mortar has a semi-closed texture. The rich cream binder contains clinker ash and inert lime.	

MORTAR ANALYSIS REPORT

JOB REFERENCE	**India House**	SAMPLE	**1**	PAGE **3**

ACID DISSOLUTION

PROCEDURE	DESCRIPTION ~ COMMENTS
10% HCL ACID DISSOLUTION	It is moderately easy to crush. There was a vigorous reaction upon dissolution.
FILTER GRADE (PORE SIZE) & TYPE	Whatman Type 1

AGGREGATE SEPARATION

BS SIEVE Mesh Size	Residue Retained in g's	Undissolved binder %	Aggregate excluding undissolved binder -gs*	Aggregate weight %	Comments	
4.75 mm	0.07	30	0.05	n/a	Clinker ash and a small amount of quartz and brick fragments.	
2.36 mm	0.36	30	0.25	n/a	Clinker ash and a small amount of quartz and brick fragments.	
1.18 mm	1.35	25	1.01	n/a	Clinker ash and a small amount of quartz and brick fragments.	

MORTAR ANALYSIS REPORT

JOB REFERENCE	**India House**	SAMPLE	**1**	PAGE **4**

0.60 mm (600 µm)	1.31	30	0.92	n/a	Clinker ash and a small amount of quartz and brick fragments.	
300 µm	2.70	15	2.30	n/a	Clinker ash and a small amount of quartz and brick fragments.	
150 µm	0.34	50	0.17	n/a	Clinker ash and a small amount of quartz and brick fragments. Alite and Belite residues.	
< 150 µm, including filter residue	1.00	50	0.50	n/a	Clinker ash and a small amount of quartz and brick fragments. Alite and Belite residues.	

The quartz aggregate is all sub-rounded. *The aggregate weight is a proportion of the combined weight of lime and aggregate, the lime being lighter.

MORTAR ANALYSIS REPORT

JOB REFERENCE	**India House**	SAMPLE	**1**	PAGE **5**

AGGREGATE CHARACTERISTICS

The primary aggregate is clinker ash and inert lime.

CONSTITUENTS OF ANALYSIS SAMPLE

MATERIAL	***WEIGHT (g)***	**COMMENTS**
A: DRY WEIGHT OF ANALYSIS SAMPLE	11.9	
B: DRY WEIGHT OF ALL INSOLUBLE	7.13	
C: DRY WEIGHT OF INSOLUBLE BINDER	1.93	
D: (B-C) DRY WEIGHT OF AGGREGATE	5.2	
E: (A-B+C)) DRY WEIGHT OF LIME & BINDERS	6.7	
F: DRY WEIGHT OF LIME	4.77	
OTHER		

MORTAR ANALYSIS REPORT

JOB REFERENCE	**India House**	SAMPLE	**1**	PAGE **6**

PROPORTIONS OF ANALYSIS SAMPLE

The sample proportions give the aggregate and carbonated or set lime relative volumes, based on the recorded weights for each sieve collection.

CEMENTITIOUS RESIDUES: FREE LIME: AGGREGATE (ASH)

1: 2.5: 2.7

PROBABLE ORIGINAL MIX

The nature of the binding matrix of the mortar sample and information gained from the analysis suggest that the mortar was probably made by volume from

1 part early cement, 2 ½ parts hydrated lime (including much inert lime), and 5 parts waste clinker ash.

Sample analysis, interpretation and report carried out by: Dr Mark Womersley.
www.mwomersleys.co.uk